



Smaltoxyl Hydro Parquet Primer

Water Based Acrylic Primer for
Floor Varnishes



Covering Power: 9 - 11 m²/lt



Drying: ½ - 1 hour



Dilution: 8 - 10 % on volume
with water



Recoatability: 2 - 4 hours



Packing: 750ml, 2,5lt

Application: Brush, Soft Roller

GENERAL CHARACTERISTICS

PARQUET PRIMER HYDRO is a water-based primer special designed for application on wood surfaces. Due to its special composition, it exhibits great adhesion and elasticity, it fills the wood pores offering ease of sanding enhancing the abrasion of wood. It dries quickly and is characterized by its ease of application.

TECHNICAL CHARACTERISTICS

| | |
|------------------------|---|
| Specific weight | 1,03 ± 0,02 kg/lt. |
| Covering power | 9 - 11 m ² /lt per layer. |
| Dilution | 8 - 10 % on volume with water. |
| Drying | ½-1 hours touch free. |
| Recoatability | Recoat able in 2-4 hours after application. These times prolong under cold and wet weather conditions. |
| VOC class | EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category A/i "One-pack performance coatings" Type WB): 140 g/L. This product contains maximum 139 g/L VOCs (ready for use product). VOC: organic volatile compounds with boiling point < 250°C. |
| Adhesion | Adhesion test, rating 1 (ISO 2409). |
| Shades | Transparent-Colourless. |



SURFACE PREPARATION

To make sure of a successful paint adhesion, the surface has to be cleaned of oil, grassy substances, cropped paints, ink, dampness etc. Sandpaper well with a suitable abrasive paper, remove dust and prime on wood. In the case of old painted wooden surfaces, the old varnish has to be removed.

APPLICATION EQUIPMENT

Brush, Soft roller.

APPLICATION

Stir well. On a properly prepared dry surface apply one or two coats PARQUET PRIMER HYDRO in the appropriate dilution. When it dries thoroughly, sand with a suitable sandpaper, clean the dust and apply 1-2 coats PARQUET HYDRO VARNISH at the desired texture.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with thinner, water and soap.

APPLICATION CONDITIONS

Temperature 8-30°C and relative humidity lower than 80%. The maximum humidity of the wood should not be more than 18% for soft woods and 15% for hard woods. Contrary conditions may degrade product's quality.

STORAGE

Store in a cool place, protect from freezing and sun exposure. Close the can well after application to keep in good condition. Recover unused paint for re-use. Reuse of paint can effectively minimize the product's life cycle environmental impact.

LABELLING

Smaltolux hydro MASTER PRIMER needs no danger symbols according to EC legislation. More information in Safety Data Sheet of the product (MSDS).

SAFETY

Read the tag on the back side of the product. Keep out of the reach of children.



The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instructions for use.