



## Corrolux Metal Effect

Metalized - Pearl Anticorrosive Enamel



**Covering Power:** 8 - 10 m<sup>2</sup>/lt



**Drying:** 2 - 3 hours



**Dilution:** 5% on volume with Smatlolux White Spirit using brush/roller, or up to 8% with Thinner No1 of Vechro when using spraygun.



**Recoatability:** 16 - 18 hours



**Packing:** 750ml, 2,5lt

**Application:** Brush, Roller, Spraygun

### GENERAL CHARACTERISTICS

Special metalized - pearl effect protective and decorative enamel with very good anticorrosive properties, suitable for indoor and outdoor metallic substrates. Ideal for protection and decoration of metallic substrates without use of anticorrosive primer. Excellent adhesion, leveling and very good drying.

### TECHNICAL CHARACTERISTICS

<b>Texture</b>	Flat embossed.
<b>Specific weight</b>	1,38-1,42 kg/lt (Metalized base).
<b>Covering power</b>	8-10 m <sup>2</sup> /lt per layer depending on the surface.
<b>Dilution</b>	Up to 5% on volume with thinner SMALTOLUX WHITE SPIRIT for application by brush or roller and 8% with Thinner No 1 of VECHRO for application with spray.
<b>Drying</b>	2-3 hours touch free depending on the weather conditions.
<b>Recoatability</b>	Recoatable 16-18 hours after application or after first layer's hardening. These times prolong under cold and wet weather conditions.
<b>VOC class</b>	"One-pack performance coatings. Anticorrosion finishes" Type SB. VOC limit = 500 gr/lt. Max VOC of product ready for use = 430 gr/lt. It fulfills the requirements of E.C. legislation after 2011. VOC: organic volatile compounds with boiling point < 250 °C.
<b>Shades</b>	Ready-made metalized - pearl shades of the product's color catalog.



## SURFACE PREPARATION

Clean the surface of dust, oil, cropped paints, rust. Sandpaper and clean well the surface.

## APPLICATION EQUIPMENT

Brush, Roller, Spraygun.

## APPLICATION

Stir well. Apply two coats CORROLUX metal effect. For better anticorrosive protection, be sure that the whole of surface has been well coated. To achieve the best anticorrosive performance, apply at least 100µm dry film, or apply firstly OXIDOL primer.

## CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with thinner, water and soap.

## APPLICATION CONDITIONS

Temperature 8-30 °C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality.

## STORAGE

Store in a cool place, protect from freezing and sun exposure. Close the can well after application to keep in good condition. Recover unused paint for re-use. Reuse of paint can effectively minimize the product's life cycle environmental impact.

## LABELLING

Read the tag on the back side of the product. Keep out of the reach of children.

More information in Material Safety Data Sheets (MSDS).



The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instructions for use.