



Gumilak Metal Chassi

Anticorrosive Primer for Metallic Surfaces



Covering Power: 12 - 14 m²/lt



Drying: 1 - 2 hours



Dilution: Up to 5% on volume with SMALTOLUX WHITE SPIRIT for application by brush or roller and for spray application up to 12% on volume with No1 thinner of VECHRO.



Recoatability: 18 hours



Packing: 750ml, 2,5lt

Application: Brush, Roller, Spraygun

GENERAL CHARACTERISTICS

Gloss alkyd paint with low VOC content, suitable for protection of cars' chassis and other metallic equipment. Gives very good adhesion, quick drying and very good water, gasoline and car oil resistance.

TECHNICAL CHARACTERISTICS

Texture	Gloss > 80 units in 60°.
Specific weight	1,19-1,24 kg/lt.
Covering power	12-14 m ² /lt per layer depending on the surface.
Dilution	Up to 5% on volume with SMALTOLUX WHITE SPIRIT for application by brush or roller and for spray application up to 12% on volume with No1 thinner of VECHRO.
Drying	1-2 hours touch free. Drying through 3-4 hours.
Recoatability	Recoatable 18 hours after application or after first layer's hardening. These times prolong under cold and wet weather conditions.
VOC class	"One-pack performance coatings. Anticorrosion finishes". Type SB. VOC limit =500 gr/lt. Max VOC of product ready for use= 490 gr/lt. It fulfills the requirements of E.C. legislation after 2011. VOC: organic volatile compounds with boiling point < 250°C.
Shades	Brown and Black.



SURFACE PREPARATION

Clean the surface of dust, oil, cropped paints, rust. Sandpaper surface before stain, especially if it was oil painted. Use solvent to clean the surface before application.

APPLICATION

Stir well till thinner is fully embodied. Apply one-two coats CHASSI COAT. For better protection, primed surfaces should be painted with the suitable finish paint such as GUMILAK metal, SMALTOLUX extra or any enamel paint from VECHRO.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with thinner, water and soap.

APPLICATION CONDITIONS

Temperature 8-30 °C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality.

STORAGE

Store in a cool place, protect from freezing and sun exposure. Close the can well after application to keep in good condition. Recover unused paint for re-use. Reuse of paint can effectively minimize the product's life cycle environmental impact.

LABELLING

More information in Material Safety Data Sheets (MSDS).

SAFETY

Read the tag on the back side of the product. Keep out of the reach of children.



The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instructions for use.