



SMALTOXYL YACHT varnish

PROTECTIVE and DECORATIVE
YACHT VARNISH



Covering Power: 12-18 m²/lt
per coat in already well-primed



Drying: 3 - 4 hours



Dilution: 5-10% on volume with
thinner SMALTOLUX WHITE SPIRIT and
10% with thinner No1 of VECHRO for
application by spray.



Recoatability: 18-24 hours



Packaging: 750ml, 2,5lt

Application: Brush, Roller, Spray-Gun

GENERAL CHARACTERISTICS

Long lasting protective and decorative yacht varnish for wooden surfaces, based on modified alkyd and polyurethane resins. Suitable for indoor and outdoor use. It contains UV filters for better UV resistance and outdoor durability. Due to its formula it protects the dried film against mildew growth and moisture. Keeps elasticity in order to follow woods movements. Great covering power and application properties. It gives a tough and elastic film.

TECHNICAL CHARACTERISTICS

| | |
|-------------------------|--|
| Texture | Gloss and satin. |
| Specific gravity | 0,96-1,00 kg/lt. |
| Covering Power | 12-18 m ² /lt per coat, in already well-primed |
| Dilution | 5-10% on volume with thinner SMALTOLUX WHITE SPIRIT and 10% with thinner No1 of VECHRO for application by spray. |
| Drying | Dry to touch in 3 - 4 hours. |
| Recoatability | 18-24 hours after application. Those times will be prolonged in cold and wet weather conditions. |
| VOC Class | "Interior/exterior trim varnishes and wood stains." Type SB. VOC limit =400 gr/lt. Max VOC of product ready for use= 395 gr/lt. VOC: organic volatile compounds with boiling point < 250° C. |
| Color shades | Gloss & Satin: Transparent- Colorless! |



SURFACE PREPARATION

Clean the surface of dust, oil, cropped paints, and dampness, sand-paper well. New wood must be primed with 1 coat of SMALTOXYL BASE for better protection against fungi and insects.

APPLICATION

Stir well till thinner is fully embodied. Apply 2 coats SMALTOXYL YACHT VARNISH on dry and absolutely clean surfaces.

CLEANNING TOOLS

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with thinner, water and soap.

APPLICATION CONDITIONS

Temperature 8-30°C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality.

STORAGE

Close well after use. Store in a cool place. Protect from sun exposure.

LABELLING

For more information please ask for the product's Safety Data Sheet (MSDS).

SAFETY

Keep out of the reach of children.

The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instructions for use.

