



Vechro Pro Relief

Acrylic with texture effects paint



Covering Power: 1 - 1,5 m² /kg



Drying: ½ - 1 hour



Dilution: Ready for use



Recoatability: 4 - 6 hours



Packing: 5kg , 15kg



Application: Thick brush, spongy roller for special texture

GENERAL CHARACTERISTICS

High quality texture emulsion paint 100% acrylic. Due to this special composition gives a perfect texture decoration surface. It can be used to paint new or old painted walls. Suitable for protection and decoration of interior and exterior surfaces such as walls, plasters and concrete surfaces if they are well primed.

TECHNICAL CHARACTERISTICS

Texture	Flat
Specific weight	1,65 - 1,70 kg/lt.
Covering power	1,0 - 1,5 m ² /kg per layer depending on the surface.
Dilution	Ready for use.
Drying	Dry to touch in ½ - 1 hour. The paint obtains its hardness after 3-4 weeks.
Recoatability	4 - 6 hours. These times could elongate under cold and wet weather conditions.
VOC class	a. "Exterior wall coatings of mineral substrate". Type WB. VOC limit = 40 gr/lt. b. "Interior matt coatings for walls and ceilings". Type WB. VOC limit = 30 gr/lt. Max VOC of product ready for use = 20 gr/lt. It fulfills the requirements of E.C. legislation after 2011. VOC: organic volatile compounds with boiling point < 250° C.
Shades	White.



SURFACE PREPARATION

Clean the surface of dust, oil, cropped paints and dampness. Sandpaper well and prime surfaces painted with white lime or new concretes with Smaltoplast Universal Primer or Vechro Pro Smaltodur, while very dirty surfaces (damp, nicotine, ink, fungi, graffiti, oil spots etc.) should be primed with special primer Smaltox Hydro or Smaltox Mono.

APPLICATION

Stir well before use. Apply one or two coats of Vechro Pro Relief by thick brush, spatula or roller without dilution. Before drying we pass over the laid surface with a special spongy roller in order to create the decoration.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot or in the paint launder. Strain well your tools from paint back to the pot and clean immediately with water and soap.

APPLICATION CONDITIONS

Temperature 8-30 °C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality. New cementinous surfaces should be dried and cured 3-4 weeks before priming.

STORAGE

Store in a cool place, protect from freezing and sun exposure. Close the can well after application to keep in good condition. Recover unused paint for re-use. Reuse of paint can effectively minimize the product's life cycle environmental impact.

LABELLING

Smaltolux hydro Master Primer needs no danger symbols according to EC legislation.

SAFETY

Read the tag on the back side of the product. Keep out of the reach of children.



The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instructions for use.