



CORROLUX HAMMERED

Gloss Hammer Finish Paint



Covering Power: 8 - 10 m²/lt



Drying: 10 - 15 minutes



Dilution: ready for use. If needed, up to 4% on volume with Thinner No1 of Vechro.



Recoatibility: 6 - 8 hours



Packing: 750ml , 2,5lt



Application: Spraygun

GENERAL CHARACTERISTICS

Special paint for industrial use, suitable either for protection or for decoration of metallic surfaces, machines, electric equipment etc. It gives a hammered surface and very good decoration results at the same time covers any defect on the surface. It creates tough film with excellent adhesion on metallic surfaces such as steel, aluminum and galvanized. Dries fast and gives excellent mechanic resistance.

TECHNICAL CHARACTERISTICS

| | |
|------------------------|---|
| Texture | Semi-gloss. |
| Specific weight | 0,97 - 1,01 kg/lt (white). |
| Covering Power | 8-10 m ² /lt per layer depending on the surface. |
| Dilution | Ready for use. If needed up to 4% on volume with Thinner No1 of VECHRO. |
| Drying | Dry to touch in 10-15 min. |
| Recoatibility | At least 6-8 hours after first coat hardening. These times elongate in bad weather conditions. |
| VOC class | <p>"One-pack performance coatings. Anticorrosion finishes"</p> <p>Type SB. VOC limit =500 gr/lt. Max VOC of product ready for use= 495 gr/lt. It fulfills the requirements of E.C. legislation after 2011. VOC: organic volatile compounds with boiling point < 250°C.</p> |
| Shades | Black and Ready made shades of VECHRO Color-card. |



SURFACE PREPARATION

Clean the surface of dust, oil, cropped paints, rust. Sandpaper surface before application and clean well from dust. On metal surfaces either apply without any preparation or prime with one coat OXIDOL PRIMER for anticorrosion protection. Prime aluminium or Galvanised surfaces with one coat WASH PRIMER.

APPLICATION

Stir well till thinner is fully embodied. Apply two coats of Corrolux Hammered.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with warm water and soap.

APPLICATION CONDITIONS

Temperature 8-30°C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality.

STORAGE

Close well after use. Store in a cool place. Protect from sun exposure.

LABELLING

More information in Material Safety Data Sheet (MSDS) .

SAFETY

Read the tag on the back side of the product. Keep out of the reach of children.



The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instructions for use.