



Smaltolux Velatoura

Undercoat for Wood Surfaces



Covering Power: 14 - 18 m²/lt



Drying: 1 - 2 hours



Dilution: 4% on volume with White Spirit using brush/roller, or up to 4% on volume with Thinner No1 when using spraygun



Recoatability: 6 - 10 hours



Packing: 750ml, 2,5lt, 5lt



Application: Brush, Roller, Spraygun

GENERAL CHARACTERISTICS

New generation undercoat based on special alkyd resins for interior and exterior use with low VOC content and lower odor during application. It can be used on surfaces of wood and MDF. Due to its special composition gives good fill, easy application and excellent brush ability, great covering, easy sanding and quick recoat ability.

TECHNICAL CHARACTERISTICS

Texture	Flat, gloss 8-10 units in 60°.
Specific weight	1,50 - 1,53 kg/lt.
Covering power	14 -18 m ² /lt per layer.
Dilution	Up to 4% on volume with SMALTOLUX WHITE SPIRIT for application by brush or roller, for airless spray application use up to 4% on volume with No 1 thinner of VECHRO.
Drying	1 - 2 hours touch free.
Recoatability	Recoatable after 6-10 hours from application or after first layer's hardening. These times prolong under cold and wet weather conditions.
VOC class	"Interior/exterior trim and cladding paints for wood and metal" Type SB. VOC limit =300 gr/lt. Max VOC of product ready for use= 290 gr/lt. The paint contains also solvents which are not considered as VOC. It fulfills the requirements of E.C. legislation after 2011. VOC: organic volatile compounds with boiling point < 250°C.
Shades	White. It could be coloured in off-white and pastel shades and only via COLOR MOODS VECHRO tinting system!



SURFACE PREPARATION

Clean the surface of dust, oil, cropped paints and dampness. Sandpaper well.

APPLICATION EQUIPMENT

Brush, roller, spraygun.

APPLICATION

Stir well. Apply one or two coats VELATOURA SMALTOLUX extra. For better protection, primed surfaces should be painted with the suitable finish paint such as SMALTOLUX extra or any enamel paint from VECHRO.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with thinner, water and soap.

APPLICATION CONDITIONS

Temperature 8-30 °C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality.

STORAGE

Store in a cool place, protect from freezing and sun exposure. Close the can well after application to keep in good condition. Recover unused paint for re-use. Reuse of paint can effectively minimize the product's life cycle environmental impact.

LABELLING

More information in Material Safety Data Sheets (MSDS).

SAFETY

Read the tag on the back side of the product. Keep out of the reach of children.



The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instructions for use.