



## Smaltoplast Cement Paint

Flat Emulsion 100% Acrylic  
Ecological Cement Paint



**Covering Power:** 11 - 13 m<sup>2</sup>/lt



**Drying:** ½ - 1 hours



**Dilution:** 8-15% on water



**Recoatability:** 4 -6 hours



**Packing:** 750ml, 3lt, 10lt



**Application:** Brush, Roller, Spraygun

### GENERAL CHARACTERISTICS

Ecological, high quality, low odor 100% acrylic CEMENT PAINT for exterior use. Suitable for walls, plasters and concrete surfaces, which have been well prepared. It has excellent whiteness, hiding and covering power, water and alkali resistance. Very good UV radiation and difficult weather conditions resistance. Easy to apply with very good leveling. Minimized content of hazardous substances. Reduced volatile organic compounds (VOCs).

### TECHNICAL CHARACTERISTICS

<b>Texture</b>	Mat velvet with sheen up to 12-16 units at 85°
<b>Specific weight</b>	1,30 - 1,50 kg/lt, depending on the shade.
<b>Covering power</b>	11 - 13 m <sup>2</sup> /lt per layer depending on the surface.
<b>Dilution</b>	8 - 15% on volume with water.
<b>Drying</b>	Dry to touch in ½ - 1 hour.
<b>Recoatability</b>	4-6 hours. These times prolong under cold and wet weather conditions.
<b>VOC class</b>	“Exterior wall coatings of mineral substrate”. Type WB. VOC limit = 40 gr/lt. Max VOC of product ready for use = 20 gr/lt. VOC: organic volatile compounds with boiling point < 250°C.
<b>Adhesion</b>	Pull off adhesion > 3.2MPa (ISO 4624)
<b>QUV weathering</b>	No cracking, flaking, blistering or chalking (ISO 16474-3, ISO 4628)
<b>Wet scrub resistance</b>	Class 1 (EN 13300 / ISO 11998)
<b>Shades</b>	White, grey & brown.



## SURFACE PREPARATION

Clean the surface of dust, oil, cropped paints and dampness. Sandpaper well. Surfaces painted with white lime or new concretes should be primed with Smaltoplast Universal Primer or SMALTODUR primer, while very dirty surfaces (damp, nicotine, ink, fungi, graffiti, oil spots etc.) should be primed with special primer SMALTOX hydro ή SMALTOX mono.

## APPLICATION

Stir well before use. Apply uniformly 1 or 2 coats SMALTOPLAST CEMENT PAINT. Minimization of paint wastage: For a surface of 10 m<sup>2</sup>, 1,6lt of paint is needed for two coats.

**Advice!** For dark shades, in order to minimize the number of coats, we propose to apply as first coat SMALTOX hydro in grey S1502 or a lighter shade of the same hue which is produced from a base with better opacity.

## CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with thinner, water and soap.

## APPLICATION CONDITIONS

Temperature 8-30 °C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality.

## STORAGE

Store in a cool place, protect from freezing and sun exposure. Close the can well after application to keep in good condition. Recover unused paint for re-use. Reuse of paint can effectively minimize the product's life cycle environmental impact.

## LABELLING

SMALTOPLAST CEMENT PAINT needs no danger symbols according to EC legislation.

This product has been awarded with the Eco-label, eco criteria 312/2014/EE product category "indoor & outdoor paints and varnishes".

## SAFETY

Read the tag on the back side of the product. Keep out of the reach of children.

The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instructions for use.