



Ultra Smaltoplast Fix

Acrylic Stucco for Woods And Walls



Covering Power: 1 - 3 m²/kg



Drying: 3 - 4 hours



Dilution: 3,5 kg water to 10 kg of compound



Recoatability: 8 - 10 hours



Packing: 5kg, 20kg

Application: Spatula

GENERAL CHARACTERISTICS

The compound is based on cement and contains also special modified acrylic resins, which make it suitable for leveling plastered surfaces and face concrete both suitable for interior and exterior masonry and cement surfaces.

It becomes easily a homogenous paste by adding water and has excellent application, filling and sanding properties. No cracks, no shrinking even at high film thickness.

TECHNICAL CHARACTERISTICS

Texture	White powder.
Particle size	99% <60 μm
Covering power	1 - 3 m ² /kg per coat, depending on the surface and the thickness of coat.
Dilution	3,5 kg water to 10 kg of compound or 7 kg water (or 1-2kg acrylic resin DUR SMALTOPLAST FIX + 5-6 kg water) to 20 kg of compound.
Recoatability	The interval between coats should at least 8-10 hours. These times may be prolonging under humid and low temperature conditions. Leave the leveled with the compound surface to dry enough before sanding and painting.
Reflectability (Y)	89,6
Hardness (shore D)	51,3
Time to live after mix	1,5 hours
Storage conditions	All products based on cement must be stored in dry interior places and if possible, on wooden pallets. Under these conditions the compound could be stored for 6-12 months.



SURFACE PREPARATION

The surface shall be clean from dust, oils, lime and as much as possible dry.

APPLICATION

Mix well until it becomes a homogenous paste. The pot life of the mix is around 4-6 hours depending on the temperature. Stir occasionally the paste but not add any more water. Apply in two coats.

A common decorative and protective coating could paint it after the proper priming. For surfaces with humidity or damaged ones with several cracks we propose to use for the homogenizing of the compound a mixture of water with the proper acrylic reinforced resin as follows: 3kg water +0.5 kg resin till 2.5kg+1kg water + resin for 10kg of compound.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with water and soap. Avoid washing materials entering into water-courses.

APPLICATION CONDITIONS

Temperature 8-300C and relative humidity lower than 80%. In hot climate conditions (temperature more than 350C) moisten the surface to be levelled.

STORAGE

All products based on cement must be stored in dry interior places and if possible on wooden palettes. Under these conditions the compound could stored for 12 months.

LABELLING

More information in Safety Data Sheets (MSDS).

SAFETY

Read the tag on the back side of the product. Keep out of the reach of children.

The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instructions for use.

