

Vinyflex Hydro Paint



Covering Power: 10-12 m²/lt



Drying: 1/2 - 1 hour



Dilution: 10 -20% with water



Recoatability: 3 - 4 hours



Packing: 3lt, 9lt, 15lt

Application: Brush, Roller, Spraygun



GENERAL CHARACTERISTICS

Vinyflex Hydro Paint is ideal for use on the ceilings of kitchens, bathrooms, bedrooms, storage rooms, stairwells and generally non-washable interiors. It has the property of leaving the pores of the roofs open, as a result of which permits the surface to breath to avoid problems of condensed moisture. It is easy to apply, has unrivaled whiteness and coverage.

TECHNICAL CHARACTERISTICS

Texture	Mat
Specific weight	1,56 - 1,60 kg/lt.
Covering power	10 -12 m²/lt per layer.
Dilution	10 - 20% on volume with water.
Drying	Dry to touch in $\frac{1}{2}$ - 1 hour. The paint adopts full resistance in washing 3-4 weeks after application.
Recoatability	3 - 4 hours. These times could elongate under cold and wet weather conditions.
VOC class	"Interior mat coatings for walls and ceilings". Type WB. VOC limit = 30gr/lt. Max VOC of product ready for use = 10gr/lt.
	VOC: organic volatile compounds with boiling point < 250°C.
Shades	White

Issued: 31/07/2018





SURFACE PREPARATION

Remove grease, oil, unsound existing paint, rust, dust and then clean thoroughly. Clean the surface of dust, oil, cropped paints, and dampness.

APPLICATION

Stir well before use. Apply two coats VINYFLEX YDROCHROMA.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with thinner, water and soap.

APPLICATION CONDITIONS

Temperature 8-30 °C and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality.

STORAGE

Store in a cool place, protect from freezing and sun exposure. Close the can well after application to keep in good condition. Recover unused paint for re-use. Reuse of paint can effectively minimize the product's life cycle environmental impact.

LABELLING

The product does not require any hazard labeling in accordance with applicable law.

SAFETY

Read the tag on the back side of the product. Keep out of the reach of children.





The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instruc-

VECHRO S.A.

Headquarters: Liosion Ave. ATHENS, zip: 111 45

Telephone: (+30) 210-4816101

Technical Data Sheet E-8051 Modified: 11/09/2023 www.vechro.gr

Issued: 31/07/2018